


Title: Colour Glass Filter (Shortpass)
Material / Specification: Schott BG3 - 465nm
Range / Description: 465FCS



Tel: +44 (0) 1622 859444
Fax: +44 (0) 1622 859555
info@knightoptical.co.uk
<http://www.knightoptical.co.uk>



INTERNAL TRANSMITTANCE FOR 3MM THICK

Title: Colour Glass Filter (Shortpass)
 Material / Specification: Schott BG3 - 465nm
 Range / Description: 465FCS

Reflection factor
 P_d 0.92
Bubble content
 Bubble class 1
Chemical resistance
 FR class 0
 SR class 1.0
 AR class 1.0

Density
 ρ [g/cm³] 2.56
Transformation temperature
 T_g [°C] 478
Thermal expansion
 $\alpha_{-30/+70^\circ\text{C}}$ [10⁻⁶/K] 8.8
 $\alpha_{20/300^\circ\text{C}}$ [10⁻⁶/K] 10.2
Temperature coefficient
 T_k [nm/°C]

Per DIN 58191 BP 368/185
 Per DIN 58191

Ionically colored glass

Limit values of τ_i
 for thickness $d = 1$ mm

Wave-length [nm]	Limits	Value from catalog curve
365	≥ 0.94	0.99
633	$\leq 5 \cdot 10^{-5}$	$8 \cdot 10^{-6}$

Refractive index n

λ [nm]	Element	n
302.1	Hg	1.55
435.8	Hg	1.52
587.6	He	1.51
1014	Hg	1.50

Tristimulus values

	d [mm]	x	y	Y	λ_d [nm]	P_e
A	1	0.161	0.042	1	457	0.96
2856	2	0.167	0.024	0	446	0.98
K	3	0.171	0.020	0	440	0.98
	5	0.177	0.017	0	427	0.97
	1	0.158	0.038	1	457	0.97
3200	2	0.164	0.022	0	447	0.98
K	3	0.167	0.018	0	442	0.99
	5	0.172	0.014	0	433	0.98
	1	0.154	0.029	2	455	0.98
D_{65}	2	0.160	0.018	1	448	0.99
	3	0.163	0.014	0	444	1.00
	5	0.166	0.011	0	438	1.00

Application notes
 Band pass filter

V
 Transmission changes are possible under the action of intense ultraviolet radiation



Tel: +44 (0) 1622 859444
 Fax: +44 (0) 1622 859555
 info@knightoptical.co.uk
 http://www.knightoptical.co.uk

(C)Knight Optical(UK)Ltd.

Transmittance τ and internal transmittance $\tau_i = 1$ mm

λ [nm]	τ	τ_i	λ [nm]	τ	τ_i
200	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	700	0.33	0.36
210	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	710	0.60	0.66
220	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	720	0.78	0.85
230	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	730	0.86	0.94
240	$3 \cdot 10^{-5}$	$3 \cdot 10^{-5}$	740	0.90	0.98
250	0.006	0.006	750	0.91	0.99
260	0.09	0.10	760	0.91	0.99
270	0.33	0.36	770	0.91	0.99
280	0.58	0.63	780	0.91	0.99
290	0.73	0.80	790	0.91	0.99
300	0.83	0.90	800	0.91	0.99
310	0.87	0.95	850	0.91	0.99
320	0.89	0.97	900	0.91	0.99
330	0.90	0.98	950	0.90	0.98
340	0.91	0.99	1000	0.86	0.94
350	0.91	0.99	1060	0.75	0.81
360	0.91	0.99	1100	0.61	0.67
370	0.91	0.98	1200	0.23	0.25
380	0.90	0.98	1300	0.11	0.12
390	0.90	0.98	1400	0.14	0.15
400	0.87	0.95	1500	0.09	0.10
410	0.84	0.92	1600	0.12	0.13
420	0.80	0.87	1700	0.13	0.14
430	0.75	0.82	1800	0.14	0.15
440	0.69	0.75	1900	0.23	0.25
450	0.61	0.66	2000	0.37	0.40
460	0.51	0.55	2100	0.48	0.52
470	0.36	0.39	2200	0.57	0.62
480	0.20	0.22	2300	0.65	0.71
490	0.09	0.10	2400	0.70	0.76
500	0.04	0.04	2500	0.71	0.77
510	0.01	0.01	2600	0.71	0.77
520	0.004	0.004	2700	0.68	0.74
530	$6 \cdot 10^{-4}$	$6 \cdot 10^{-4}$	2800	0.55	0.60
540	$3 \cdot 10^{-4}$	$3 \cdot 10^{-4}$	2900	0.53	0.58
550	$6 \cdot 10^{-4}$	$6 \cdot 10^{-4}$	3000	0.52	0.57
560	0.002	0.002	3200	0.45	0.49
570	$9 \cdot 10^{-4}$	0.001	3400	0.38	0.41
580	$9 \cdot 10^{-5}$	$1 \cdot 10^{-4}$	3600	0.37	0.40
590	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	3800	0.39	0.42
600	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	4000	0.42	0.46
610	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	4200	0.37	0.40
620	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	4400	0.23	0.25
630	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	4600	0.07	0.08
640	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	4800	0.03	0.03
650	$<1 \cdot 10^{-5}$	$<1 \cdot 10^{-5}$	5000	0.007	0.008
660	$5 \cdot 10^{-5}$	$5 \cdot 10^{-5}$	5200	$3 \cdot 10^{-4}$	$3 \cdot 10^{-4}$
670	$6 \cdot 10^{-4}$	$6 \cdot 10^{-4}$			
680	0.01	0.01			
690	0.09	0.10			